

DESCRIPTION

NEXON WP PU 350 LV; One component, PU based elastic and economic liquid waterproofing membrane. It produces a durable and highly elastic membrane by curing the humidity.

FEATURES

- Economical,
- Simple application (brush, roller or airless spray),
- When applied forms seamless membrane without joints,
- As it is pure polyurethane, it can continually contact with water.
- Maintains its mechanical properties over a temperature span of -40°C to +80°C,
- Provides water vapor permeability, so the surface can breathe,
- Even the membrane gets damaged, it can be easily repaired locally within minutes.
- Resistance to chemicals,

TYPICAL APPLICATIONS

- Gypsum and cement boards,
- Indoors and outdoors,
- Non exposed roofs,
- Wet Areas
- Bathrooms,
- Undertile waterproofing,
- Asphalt EPDM membranes,

SURFACE PREPARATION

All surfaces must be free of oil, grease and moisture before the application. Clean the surface using a high pressure washer and remove oil, grease and wax contaminants, cement laitance, loose particles and mould release agents must be removed. Fill surface irregularities with the relevant product.

PRIMING

Prime very absorbent and brittle concrete or brittle cement screed surfaces with **NEXON PU PRIMER SC 100** or **NEXON EPOXY PRIMER 120 SF** (Humidity of the concrete should not exceed %5). Or for damp concretes **NEXON PU PRIMER SC 100** or **NEXON EPOXY PRIMER SF 300** is suggested for moisture barrier. Prime non-absorbent surfaces like metal, ceramic tiles and old coatings with **NEXON PU TILE PRIMER**. Apply the material with roller or brush in two, at least, coats. Do not exceed 48 hours between coats. For a better interlayer adhesion, use **NEXON PU PRIMER SC100**.

MIXING - THINNING

NEXON WP PU 350 LV; Power first mix the portion to obtain a smooth, homogenous condition. After the stirring is complete, then continue mixing slowly several minutes.

APPLICATION

NEXON WP PU 350 LV; Apply the mixture with a brush or a roller in minimum two layers. After first layer is applied minimum 12 hours max 24 hours, second layer should be applied. Do not exceed 48 hours between each coats. Do not allow coating to remain in the application equipment longer than 2 hours.

CONSUMPTION

Each layer min.: 0,6 - 0,75 kg/m²

Min. two coats should be applied

Total min. consumption: 1,2 - 1,5 kg/m²

PACKAGING AND SHELF LIFE

5 Kg - 25 Kg

Can be kept for 12 months minimum in the original unopened pails in dry places and at temperatures of 5-25 °C. Once opened, use as soon as possible.

PRECAUTION

Apply in well-ventilated, no smoking areas, away from naked flames. In closed spaces use ventilators and carbon active masks. Hands and eyes must be protected with gloves and protective glasses. Case of eye contact, rinse eyes with plenty of water for the material and consult a doctor immediately. Keep in mind that solvents are heavier than air so they creep on the floor. The MSDS (Material Safety Data Sheet) is available on request.

NOTE

This is not a specification and all information is given in good faith. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult Nexon Polymers for detailed recommendations. The new edition of the technical data sheet supersedes the previous technical information and renders it invalid.

SPECIFICATION DATA

Coating type	1K Polyurethane
Color	Grey
Density ASTM D 1475/EN ISO 2811-1(20°)	1,43 gr/cm ³ ±0.05
Viscosity ASTM D 2196/EN ISO 3219(25°)	3000-5000cp
Packaging	5 Kg - 25 Kg
Water Vapor Permeability (ASTME96)	0,8 gr/ m ² per hour
Gloss	Semi Gloss
Application Temperature	+5 °C to +35°C
Thinner	Thinning is not recommended
Temperature resistance	100 days at 80 °C & 200°C Dry (shock)
Shelf Life	12 Months
Theoretical spreading rate	1,2-1,5 kg/m ²
Hardness ASTM D2240,DIN 53505,ISO R 868	60 (Shore A)
Elongation Percentage (23°C)(ASTM D 412)	≥ %400
QUV (ASTM G53)	2000 hours
Tensile Force at Break (23°C)(ASTM D 412)	≥ 5,5 N/mm ²
Adherence on Concrete (23°C)(ASTM D 903)	≥ 2 N/mm ²
Method of application	Airless spray, roller and brush
Drying Time Potlife and drying time depends on temperature and quantities mixed	23°C, %55 RH Touch dry: 4 Hrs Recoating: 8-24 Hrs Fully cured: 7 days

**MORAN İNŞAAT SANAYİ VE TİCARET ANONİM ŞİRKETİ**

Head Office: MERKEZ MAH.29 EKİM CAD.VİZYON PARK SİT.A1

BLK.OFİS-106 YENİBOSNA / BAĞÇELİEVLER

Phone : +90 542 239 23 24 - +90 212 603 28 27

Email : trade@morancorp.com

www.morantrade.net